

# SN63/PB37 SOLDER ALLOY

## **FEATURES**

- Liquidus 183°C (361°F)
- High Purity
- Low Dross
- Ocomplies with IPC J-STD-006 Current Rev

## DESCRIPTION

Sn63/Pb37 Electropure<sup>TM</sup> is alloyed in a proprietary method resulting in a low drossing, high wetting solder. The Electropure process reduces suspended oxides in the solder, thus reducing drossing, improving flow, and reducing bridging during soldering. Applications include wave and selective soldering and plating where Sn63/Pb37 Electropure is primarily used as a coating for corrosion protection, and as a base for soldering.

#### AVAILABILITY

Sn63/Pb37 Electropure is available in 1.1 kg (2.5 lb) bars, 3 kg AIM Safety Bar and Solid Wire. Sn63/Pb37 Electropure is also available in AIM flux cored wire solder and solder paste.

# **TYPICAL ALLOY COMPOSITION**

Typical Alloy Composition		
Sn: 63.0	Pb: 37.0	

# **TYPICAL MELTING TEMPERATURE**

Melting Temperature		
183°C (361°F) Eutectic		



#### **HANDLING & STORAGE**

Parameter	Time	Temperature
Shelf Life	7 years	Room Temperature

Solid wire and bar solder products have a shelf life of 7 years under proper storage conditions. For other product categories, refer to those product specific TDS's. Consult the SDS for specific handling procedures.

#### FLUX COMPATIBILITY

Sn63/Pb37 Electropure bar solder is compatible with all RMA, no clean and water soluble electronic grade fluxes.

## CLEANING

Refer to data sheets provided by the flux manufacturer.

## SAFETY

Use with adequate ventilation and proper personal protective equipment. Refer to the accompanying Safety Data Sheet for any specific emergency information. Do not dispose of any hazardous materials in non-approved containers.

**DISCLAIMER** The information contained herein is based on data considered accurate and is offered at no charge. Product information is based upon the assumption of proper handling and operating conditions. Liability is expressly disclaimed for any loss or injury arising out of the use of this information or the use of any materials designated. Please refer to http://www.aimsolder.com/terms-conditions to review AIM's terms and conditions.